

Product Name : Automatic PreStretch

Product Form : PE Film

Product Colour : Naturel

Vatan Laboratory Values

Test Metod	ASTM D 882		ASTM D 882		ASTM D 1709-09
	Strength (N/mm ²) (Min.)		Elongation (%) (Min.)		
	MY	MYD	MY	MYD	
Thickness					Dart Drop (g)
7 mic	110	21	160	720	55
8 mic	115	22	165	730	55
9 mic	120	22	170	740	60
10 mic	125	23	175	750	60
12 mic	130	23	180	760	70

Main Features Of The Product :

- The tolerances of the film; Thickness: $\pm 3\%$, width $\pm 1\text{mm}$, length $\pm 2\text{m}$,
- Film width is min. 38cm, max 43 cm.
- Length of film can be;
-Min. 900mt, max 3000mt for Automatic PreStretch.
- Does not include the forbidden materials set forth in ROHS directive.
- Does not include heavy metals and the materials included in the REACH regulation.

Notes :

- The films should be carried as packaged.
- The films should be avoided about damages.
- The films should be kept in dry environment.
- The films should not be contacted with water.
- Films to be used in extremely cold weather, had to be kept in production area for 12 hours to be able to actify the glue in the film.
- Films should consumed in 6 months in order to avoid problems caused of seasonal changes.