

Product Name : Automatic Stretch
Product Form : PE Film
Product Colour : Transparent and all colors

Vatan Laboratory Values						Elongation Values
Test Metod	ASTM D 882		ASTM D 882		ASTM D 1709-09	Vatan Plastik Metod
Thickness	Strength (N/mm ²) (Min.)		Elongation (%) (Min.)		Dart Drop (g)	Elongation (%)
	MD	TD	MD	TD		
12 mic	35	18	375	600	50	150
15 mic	36	18	410	620	50	
17 mic	37	19	450	650	50	
20 mic	37	19	475	675	60	
23 mic	38	20	500	700	70	
25 mic	39	21	530	710	80	
30 mic	39	21	550	730	90	
35 mic	40	22	600	750	100	

Main Features Of The Product :

- The tolerances of the film; Thickness: $\pm 3\%$, width $\pm 1\%$ mm, length $\pm 2\%$ m,
- Film width min.25cm, max 150cm.
- Roll film length min. 1.000mt, max 2.500mt.
- Does not include the forbidden materials set forth in ROHS directive.
- Does not include heavy metals and the materials included in the REACH regulation.

Notes :

- The films should be carried as packaged.
- The films should be avoided about damages.
- The films should be kept in dry environment.
- The films should not be contacted with water.
- Films to be used in extremely cold weather, had to be kept in production area for **12 hours** to be able to actify the glue in the film.
- Films should consumed in **6 months** inorder to avoid problems caused of seasonal changes.